

Electrically Conductive Elastomer CE-005



CE-005 is Shore A 70 durometer hardness silicone elastomer filled with carbon particles as the conductive and shielding media. **CE-005** has good shielding properties and conductivity. This material has excellent sealing at temperature extremes, is ozone resistant and has a long shelf life. **CE-005** is a good choice for applications that require static dissipation. This material can be supplied as, molded parts, extruded shapes, and die cut parts or as standard sheet stock. Contact our main office for additional information regarding your specific application.

Elastomer:	Silicone
Filler Material:	Carbon
Color:	Black

Electrical Properties

Test Method

Volume Resistivity (ohm-cm) (as supplied)	Max.	4.000	MIL-DTL-83528F	(Para. 4.5.11)
Shielding Effectiveness (db)	Min.		MIL-DTL-83528F MIL-STD-285	(Para. 4.5.12)
100 MHz (E-Field)		70		
500 MHz (E-Field)		60		
2 GHz (Plane Wave)		40		
10 GHz (Plane Wave)		30		

Electrical Stability

After Heat Aging (ohm-cm)	Max.	7.000	MIL-DTL-83528F	(Para. 4.5.15)
After Break (ohm-cm)	Max.	7.000	MIL-DTL-83528F	(Para. 4.5.9)
During Vibration (ohm-cm)	Max.	N/A	MIL-DTL-83528F	(Para. 4.5.13)
After Vibration (ohm-cm)		N/A		
After Exposure to EMP (ohm-cm) (0.9 KAMP/inch of Perimeter)	Max.	N/A	MIL-DTL-83528F	(Para. 4.5.16)

Physical Properties

Specific Gravity (+/-0.25)		1.3	ASTM D792	(MIL Para. 4.5.3)
Hardness (Shore A) (+/-7)		70	ASTM D2240	(MIL Para. 4.5.4)
Tensile Strength (PSI)	Min.	700	ASTM D412	(MIL Para. 4.5.6)
Elongation (%)	Min.	100	ASTM D412	(MIL Para. 4.5.6)
	Max.	300		
Tear Strength (PPI)	Min.	50	ASTM D624	(MIL Para. 4.5.8)
Compression Set (%)	Max.	45	ASTM D395	(MIL Para. 4.5.7)
Upper Operating Temp. (°C)	Max.	+160		
Lower Operating Temp (°C)	Min.	-55	ASTM D1329	(MIL Para. 4.5.14)
Compression Deflection (%)	Min.	3.5	ASTM D575	(MIL Para. 4.5.5)
Fluid Immersion		NS	MIL-DTL-83528F	(Para. 4.5.17)

SUR=Survivable NS=Not Survivable

Note: For compression data please contact sales@nedc.com or refer to www.nedc.com.

Performance of conductive elastomers varies on application. NEDC Sealing Solutions cannot guarantee that the above specifications will be met in your application. If you need assistance in testing your application, do not hesitate to contact us for further information.

NEDC Sealing Solutions • 96 Milk Street, Methuen, MA 01844 • 800-224-6332 • www.nedc.com

Material Bulletin 092515-001