



CHEMICAL RESISTANCE GUIDE



NEDC Sealing Solutions, Inc.
American EMI Solutions, a Division of NEDC
42 Newark Street | Haverhill, MA 01832

Tel: 800.224.6332 | Fax: 978.374.9912
www.nedc.com | sales@nedc.com



THE GENERAL CHEMICAL RESISTANCE OF VARIOUS ELASTOMERS

This chart is offered as a general guide, including the suitability of various elastomers for service in these chemicals and fluids. The ratings are based for the most part, on published literature of various polymer suppliers, rubber manufacturers, and in some cases, the considered opinion of experienced compounders. We cannot guarantee their accuracy nor assume responsibility for use thereof. Many factors must be considered in using a rubber part in service. The most important as we see them are:

1. *The temperature of Service:* Higher temperatures increase the affect of all chemicals on polymers. The increase varies with the polymer and the chemical. A compound quite suitable at room temperature might fail miserably at elevated temperature.
2. *Conditions of Service:* A compound that swells badly might still function as a static seal yet fail in any dynamic application.
3. *The Grade of the Polymer:* Many types of polymers are available in different grades that vary greatly in chemical resistance.
4. *The Compound Itself:* Compounds designed for other outstanding properties may be poorer in performance in a chemical than one designed especially for fluid resistance.
5. *The Durometer:* In general, the harder a compound the better its resistance.

In light of the above factors, it is always best to test.

Fluid Chart Key	General Purpose Non-Oil Resistant					General Purpose - Oil Resistant					Specialty Elastomers			
	(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)
Common Name	Natural Rubber	SBR or BUNA-S	Butyl	EPDM or EP Rubber	Nitrile, NBR or BUNA-N	Epichlorohydrin	Neoprene	Hypalon	Urethane	Polysulfide	Silicone	Fluoro Silicone	Fluoro Carbon	Polyacrylate
ASTM D 1418	NR	SBR	IIR	EPDM, EPM	NBR	CO, ECO	CR	CSM	AU, EU	T	VMQ	FVMQ	FKM	ACM
Designation Chemical Name	Polyisoprene	Styrene Butadiene	Isobutylene Isoprene	Ethylene Propylene Copolymer	Acrylonitrile Butadiene	Epichlorohydrin	Chloroprene	Chlorosulfonated Polyethylene	Polyester, or Polyether Urethane	Polysulfide	Polydimethyl-Siloxane	Fluorovinyl Methyl Siloxane	Fluorinated Hydrocarbon	Copolymer of Ethyl and Butyl Acrylate
Generally Resistant To	Most Moderate Chemicals Wet or Dry, Organic Acids, Alcohols Ketones Aldehydes	Similar to Natural Rubber	Animal and Vegetable Fats, Oils, Greases, Ozone, Strong and Oxidizing Chemicals	Animal and Vegetable Oils, Ozone, Strong and Oxidizing Chemicals	Many Hydrocarbons, Fats, Oils, Greases, Hydraulic Fluids, Chemicals	Similar to Nitrile with Ozone Resistance	Moderate Chemicals and Acids, Ozone, Oils, Fats, Greases, Many Oils and Solvents	Similar to Neoprene with Improved Acid Resistance	Ozone, Solvents, Thinners, Moderate Chemicals, Fats, Oils, Greases	Ozone, Oils, Solvents, Thinner, Ketones, Esters, Aromatic Hydrocarbons	Moderate or Oxidizing Chemicals, Ozone, concentrated Sodium Hydroxide	Moderate or Oxidizing Chemicals, Ozone, Aromatic Chlorinated Solvents, Bases	All Aliphatic, Aromatic and Halogenated Hydrocarbons, Acids, Animal and Vegetable Oils	Ozone, Extreme Pressure, Lubricants, Hot Oils, Petroleum Solvents, Animal and Vegetable Fats
Generally Attacked By	Ozone, Strong Acids, Fats, Oils Greases, Most Hydrocarbons	Similar to Natural Rubber	Petroleum Solvents, Coal Tar Solvents, Aromatic Hydrocarbons	Mineral Oils and Solvents, Aromatic Hydrocarbons	Ozone* Ketones, Esters, Aldehydes, Chlorinated and Nitro Hydrocarbons	Ketones, Esters, Aldehydes, Chlorinated and Nitro Hydrocarbons	Strong Oxidizing Acids, Esters, Ketones, Chlorinated, Aromatic and Nitro Hydrocarbons	Concentrated Oxidizing Acids, Esters, Ketones, Chlorinated Aromatic and Nitro Hydrocarbons	Concentrated Acids, Esters, Ketones, Chlorinated and Nitro Hydrocarbons	Mercaptans, Chlorinated Hydrocarbons, Nitro Hydrocarbons, Ethers, Amines, Heterocyclics	Many Solvents Oils, Concentrated Acids, Dilute Sodium Hydroxide	Brake Fluids Hydrazine Ketones	Ketones, Low Mole Weight, Ester and Nitro Containing Compounds	Water, Alcohols, Glycols, Alkali, Esters, Aromatic Hydrocarbons, Halogenated Hydrocarbons, Phenol

*Except PVC Blends



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:

A - Recommended - Little or minor effect

B - Minor to moderate effect - Rubber parts probably still useful in many applications

C - Moderate to severe effect - Rubber parts perhaps still useful in limited applications

U - Not recommended

Blank - No data or insufficient evidence - It should be noted that it is not expected that a polymer unrated would perform better than those that are rated.

Fluid Resistance Key	(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Acetaldehyde	C	U	A	A	U		C	C	U	C	A	U	U	U
Acetamide	C	C	A	A	A	B	B	B	U	B	B	A	B	U
Acetic Acid, Glacial	B	C	B	A	C	U	C	C	U	B	B	C	B	U
Acetic Acid, 30%	B	B	B	A	B	U	A	A	U	B	A	B	B	U
Acetic Anhydride	B	B	B	B	C		A	A	U	B	C	B	U	U
Acetone	B	B	A	A	U	U	B	B	U	C	B	U	U	U
Acetophenone	C	U	A	A	U	U	U	U	U	U	U	U	U	U
Acetyl Chloride	B	B	A	A	B		B	B			B	U	A	
Acetylene	U	C	U	U	U		C	C		C	U	U	A	
Acrylonitrile														
Adipic Acid														
Alkazene														
Alum-NH3-Cr-K	A	A	A	A	A	B	A	A	B	U	A	B	B	U
Aluminum Acetate	A	B	A	A	B	A	B	A	U	U	U	U	A	U
Aluminum Chloride	A	A	A	A	A	A	A	A	U	B	A	A	A	A
Aluminum Fluoride	B	A	A	A	A	A	A	A	U	B	B	A	A	
Aluminum Nitrate	A	A	A	A	A	A	A	A	U	B	B	A	A	
Aluminum Phosphate	A	A	A	A	A	A	A	A	U	A	A	A	A	
Aluminum Sulfate	A	B	A	A	A	A	A	A	U	A	C	A	A	U
Ammonia Anhydrous	A	A	A	A	A	A	A	B	U	A	C	A	A	
Ammonia Gas (Cold)	A	A	A	A	A		A	A	U	A	A	A	U	
Ammonia Gas (Hot)														
Ammonium Carbonate	A	A	A	A	U	B	A	A	U	B	A	U	A	
Ammonium Chloride	A	A	A	A	A	A	A	A	U	B	A	A	A	
Ammonium Hydioxide	U	U	A	A	U	B	A	A	A	U	A	B	B	U
Ammonium Nitrate	C	A	A	A	A	A	B	A	U					A
Ammonium Nitrite	A	A	A	A	A	A	A	A	U					U
Ammonium Persulfate	A	U	A	A	U	A	A	A	U	A	A			
Ammonium Phosphate	B	A	A	A	A	A	A	A	U	A	A			
Ammonium Sulfate	A	B	A	A	A	A	A	A	U	A	A			
Amyl Acetate	B	C	A	A	U	U	U	U	U	U	U	U	U	U
Amyl Alcohol	B	B	A	A	U	B	A	A	U	U	A	U	B	U
Amyl Borate	U	U	U	U	U	U	U	U	U	U	A	U	A	U
Amyl Chloronaphthalene	U	U	U	U	U	U	U	U	U	U	B	A	A	U
Amyl Naphthalene	U	U	U	U	U	U	U	U	U	U	A	A	A	B
Aniline	U	U	B	B	U	U	U	C	U	C	C	C	C	U
Aniline Dyes	B	B	B	B	B	B	U	B	U	B	B	B	B	U
Aniline Hydrochloride	B	C	B	B	B	B	U	B	U	B	B	B	B	U
Animal Fats	U	U	B	B	A	A	A	B	B	A	B	A	A	A
Ansul Ether	U	U	C	C	C	C	A	C	B	A	C	C	C	U
Aqua Regia	U	U	U	C	C	C	U	C	U	U	B	B	B	U
Arochlor(s)	B	A	A	A	A	A	A	A	A	A	A	A	A	C
Arsenic Acid	B	A	A	A	A	A	A	A	A	A	A	A	A	
Arsenic Trichloride														
Askarel	U	U	U	U	B	U	U	U	U	U	U	B	A	U
Asphalt	U	U	U	U	B	A	C	C	B	A	U	B	A	B
Barium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Sulfide	A	B	A	A	A	A	A	A	A	B	A	A	A	U
Beer	A	A	A	A	A	A	A	A	A	U	A	A	A	U
Beet Sugar Liquors	A	A	A	A	A	U	U	A	A	U	A	A	A	U
Benzene	U	U	U	U	U	U	U	U	U	C	U	A	A	U
Benzenesulfonic Acid														
Benzaldehyde	U	A	A	U	U	U	U	U	U	U	U	U	U	U
Benzyl Alcohol		B	B	U	U	U	A	B	U	U	B	B	B	A
Benzyl Benzoate			B	B			U							A
Benzyl Chloride														A
Benzoic Acid														A
Blast Furnace Gas	U	U	A	A	U	U	U	C	A	U	B	B	B	A
Bleach Solutions														A
Borax	B	B	A	A	B	A	A	A	A	B	B	B	A	B
Bordeaux Mixture	B	B	A	A	A	A	A	A	A	B	B	B	A	B
Boric Acid	A	A	A	A	A	A	A	A	A	U	A	A	A	U
Brine			A	A	A	A								
Bromine - Anhydrous														
Bromine Trifluoride	U	U	U	U	U	U	U	U	U	U	U	U	U	U
Bromine Water														
Bromobenzene	U	U	U	U	U	U	U	U	U	U	C	U	A	U



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:

A - Recommended - Little or minor effect
 B - Minor to moderate effect - Rubber parts probably still useful in many applications
 C - Moderate to severe effect - Rubber parts perhaps still useful in limited applications
 U - Not recommended
 Blank - No data or insufficient evidence - It should be noted that it is not expected that a polymer unrated would perform better than those that are rated.

Fluid Resistance Key	(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Bunker Oil	U	U	C	C	A	U	B	B	B	A	B	A	B	A
Butadiene														
Butane	U	U	U	U	A	A	A	A	A	A	A	A	A	A
Butter			B	A	A	A	B	B	A		A	A	A	A
Butyl Acetate			B	B	A	A	B	B	A		A	A	A	A
Butyl Acetyl Ricinoleate			A	A	A		B	B			B	A	A	A
Butyl Acrylate			U	U	U									
Butyl Alcohol	A	A	B	B	A		A	A	U	B	B	A	A	U
Butyl Amine	U	U	U	U	C		U	U	U	U		A	U	U
Butyl Benzoate			A	A	A		U	U				A	A	A
Butyl Carbitol			A	A	A		B	B				A	A	A
Butyl Cellosolve			A	A	C		B	B				U		
Butyl Oleate	U	U	B	B				U	U			B	A	A
Butyl Stearate	U	U	B	B	B							B	B	A
Butylene	U	U	U	U	B		C	C				B	A	A
Butyraldehyde	C	C	B	B	C		C	C			C	U	U	U
Calcium Acetate	A	U	A	A	B		B	B				A	U	U
Calcium Bisulfite	U	U	U	U	A		A	A				A	A	A
Calcium Chloride	A	U	A	A	A		A	A				A	A	A
Calcium Hydroxide	A	U	A	A	A		A	A				A	A	A
Calcium Hypochlorite	U	U	A	A	C		C	C				B	A	U
Calcium Nitrate	A	A	A	A	A		A	A				B	A	A
Calcium Sulfide	B	B	A	A	B		A	A				B	A	A
Cane Sugar Liquors	A	A	A	A	A		A	A				A	A	A
Carbamate	U	U	B	B	C		B	B				B	A	U
Carbitol	B	B	B	B	B		B	B				B	B	U
Carbolic Acid	U	U	B	B	U		C	C				U	A	A
Carbon Bisulfide	B	B	U	U	C		U	U				A	A	A
Carbon Dioxide	A	B	B	B	A		A	A				A	A	A
Carbonic Acid	B	B	A	A	A		A	A				A	A	B
Carbon Monoxide	B	B	A	A	A		A	A				A	A	A
Carbon Tetrachloride	U	U	U	U	C		B	B				U	A	A
Castor Oil	A	A	B	B	A		A	A				A	A	A
Cellosolve	U	U	B	B	B		U	U				U	C	U
Cellosolve Acetate	U	U	B	B	B		U	U				B	U	U
Cellulube			A	A	A									
Chlorine (Dry)	U	U	C	C	B		C	B				A	A	U
Chlorine (Wet)	U	U	C	C	U		U	U				B	B	A
Chlorine Dioxide	U	U	U	U	U		U	U				B	A	U
Chlorine Trifluoride	B	U	U	B	A		U	B				B	U	U
Chloroacetone														
Chloroacetic Acid	U	U	B	B	U		U	U						
Chlorobenzene	U	U	U	B	B		U	U						
Chlorobromomethane	U	U	B	B	U		U	U						
Chlorobutadiene	U	U	U	U	U		U	U						
Chlorododecane	U	U	U	U	U		U	U						
Chloroform	U	U	U	U	U		U	U				U	B	A
O-Chloronaphthalene	U	U	U	U	U		U	U				B	A	A
1-Chloro 1-Nitro Ethane	U	U	U	U	U		U	U				C	C	U
Chlorosulfonic Acid	U	U	U	U	U		U	U				B	C	U
Chlorotoluene	U	U	U	U	U		U	U				A	C	A
Chrome Plating Solutions	U	U	U	U	U		U	U				B	B	A
Chromic Acid	U	U	C	C	U		U	U				C	C	A
Citric Acid	A	A	A	A	A		A	A				A	A	A
Cobalt Chloride	A	A	A	A	A		A	A				A	A	U
Cocconut Oil	U	U	A	A	A		B	B				A	A	A
Cod Liver Oil	U	U	A	A	A		B	B				B	A	A
Coke Oven Gas	U	U					B	B				B	B	A
Copper Acetate			A	A	B		A	A						
Copper Chloride	A	A	A	A	A		A	A				A	A	A
Copper Cyanide	A	A	A	A	A		A	A				A	A	A
Copper Sulfate	B	B	A	A	A		A	A				A	A	U
Corn Oil	U	U	B	C	A		B	B				A	A	A
Cottonseed Oil	U	U	C	A	A		B	B				A	A	A
Creosote	U	U	U	U	B		C	C				B	A	A
Cresol	U	U	U	U	C		C	C				B	A	A
Cresylic Acid	U	U	U	U	C		C	C				B	A	B
Cumene	U	U	U	U	A		U	U				B	A	A
Cyclohexane	U	U	U	U	A		U	U				B	A	B



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:		Chemical Resistance Guide													
		Chemical Resistance Guide													
		(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Cyclohexanol	B	U	U	U	U	B	U	A	A	B	B	A	U	A	U
Cyclohexanone		B	B	B	B	B	U	U	U	B	B	B	U	A	U
P-Cymene								U	U		B		B	A	A
Decalin	U	U						U	U		B			A	A
Decane	U	U						U	U		A			A	A
Denatured Alcohol	A	A	A	A	A	B	A	A	A	B	C	B	A	A	A
Detergent Solutions	B	B	A	A	A	A	A	A	A	U	A	A	A	A	U
Developing Fluids	A	B	B	B	B	A	A	A	A	A	A	A	A	A	A
Diacetone				A	A					B			U	U	
Diacetone Alcohol	U	U		A	A	U	U	A	A	B	B		A		
Dibenzyl Ether	U	U	B	B	U	U	U	B	B	B	B				
Dibenzyl Sebacate		B	B	B	B	U	U	U	U	U	B	C	C	B	U
Diethyl Amine	U	U	U	U	U	U	U	U	U	U	U	C	C	U	U
Diethyl Ether	U	U	C	C	C	B	B	C	C	B	A	U	C	C	C
Diethyl Phthalate	C	U	B	A	U	U	U	U	U	C	C	B	B	B	U
Dibutyl Sebacate	U	U	B	B	U	U	U	U	U	U	B	B	B	B	U
O-Dichlorobenzene	U	U	U	U	U	U	U	U	U	U	A	U	B	A	C
Dichloro-Isopropyl Ether	U	U	C	C	U	U	U	U	U	B	A	U	C	B	B
Dicyclohexylamine	U	U				C						C			
Diesel Oil	U	U	U	U	U	A	A	B	B	B	A	U	A	A	A
Diethylamine	B	B	B	B	C	U	U	C	C	C	B	B	U	U	U
Diethyl Benzene	B	U	U	U	U	U	U	C	C	C	B	U	A	A	U
Diethyl Ether	U	U	U	U	U	U	U	C	C	A	A	U	C	U	C
Diethylene Glycol	A	A	A	A	A	A	A	A	A	U	U	B	A	A	U
Diethyl Sebacate		B	B	B	U	U	U	U	U	U	B	B	B	B	U
Diisobutylene	U	U	U	A	A	U	U	U	U	U	B	B	C	A	A
Diisopropyl Benzene		U	U	U	U	U	U	U	U	U	U	B	B	B	U
Diisopropyl Ketone		A	U	A	A	U	U	U	U	U	B	B	B	B	U
Dimethyl Aniline	U	U	U	B	B			U				B		U	U
Dimethyl Formamide	U	U	B	B	B	U	U	C	U	U	B	B	B	B	U
Dimethyl Phthalate	U	U	B	U	U	U	U	U	U	U	B	B	B	B	C
Dinitrotoluene		B	B	B	B	B	B	U	U	U	B	C	B	B	B
Diocetyl Phthalate		B	B	B	B	B	B	U	U	U	B	C	B	B	B
Diocetyl Sebacate	U	U	B	B	B	U	C	U	U	B	C	C	C	B	U
Dioxane	U	U	C	B	B	U	B				A	B	C	A	A
Dioxolane		U	U	C	B	B	B				B	B	B	B	U
Dipentene															
Diphenyl															
Diphenyl Oxides															
Dowtherm Oil	U	U	U	U	A	U	U	U	U	B		C	B	A	A
Dry Cleaning Fluids	U	U	U	U	U	C	U	U	U	B		B	A	B	A
Epichlorohydrin	U	U	B	B	B	A	B	B	B	B	A	B	U	A	U
Ethane	B	B	B	B	B	B	B	B	B	C	B	B	A	A	U
Ethanolamine	B	B	B	B	B	B	B	B	C	C	C	B	B	U	U
Ethyl Acetate	B	B	B	B	B	B	B	B	C	C	C	B	B	B	U
Ethyl Acetoacetate	C	C	B	B	B	U	U	C	C	C	B	B	B	B	U
Ethyl Acrylate	A	A	B	B	B	A	U	A	A	B	B	B	A	U	U
Ethyl Alcohol	U	U	A	U	A	U	U	A	U	B	A	A	A	A	U
Ethyl Benzene	A	U	B	B	B	B	B	B	B	B	C	B	A	A	A
Ethyl Benzoate															
Ethyl Cellosolve															
Ethyl Cellulose	B	B	B	A	B	A	A	B	B	B	B	U	U	U	U
Ethyl Chloride	B	B	U	A	B	A	A	C	C	C	B	B	A	A	C
Ethyl Chlorocarbonate	U	U	U	U	U	U	U	U	U	U	U	U	U	B	A
Ethyl Chloroformate														B	A
Ethyl Ether				C	C	C	B	U	U	B	A	C	C	U	U
Ethyl Formate	U	U	B	B	U	U	U	B	B				A	A	A
Ethyl Mercaptan	U	U	U	U	U	U	U	U	U				A	A	A
Ethyl Oxalate	A	A	A	A	A	U	U	C	U	U	A	U	B	A	A
Ethyl Pentochlorobenzene	U	U	U	U	U	U	U	C	U	U	A	U	B	A	A
Ethyl Silicate	B	B	B	A	A	A	A	A	A	A	A	B	A	A	A
Ethylene								A						A	A
Ethylene Chloride				C	C								C	C	A
Ethylene Chlorhydrin	B	B	A	A	A	U	U	A	B	B	B	B	C	B	A
Ethylene Diamine	B	U	C	C	C	U	U	A	U	U	U	U	U	U	U
Ethylene Dichloride													C	C	A
Ethylene Glycol	A	A	A	A	A	U	U	A	U	U	B	C	A	A	U
Ethylene Oxide			C	C	C	U	U	U	U	U	C	C	C	A	U
Ethylene Trichloride			C	C	C	U	U	U	U	U	C	C	C	C	A

CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:

A - Recommended - Little or minor effect

B - Minor to moderate effect - Rubber parts probably still useful in many applications

C - Moderate to severe effect - Rubber parts perhaps still useful in limited applications

U - Not recommended

Blank - No data or insufficient evidence - It should be noted that it is not expected that a polymer unrated would perform better than those that are rated.

Fluid Resistance Key	(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Fatty Acids	C	C	U	U	B		B	B		U	C		A	
Ferric Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	
Ferric Nitrate	A	A	A	A	A	A	A	A	A	A	C	A	A	
Ferric Sulfate	A	A	A	A	A	A	A	A	A	A	C	A	A	
Fish Oil											B	A	A	A
Fluoroboric Acid	A	A	A	A	A		A	A		U	U		B	
Fluorine (Liquid)	U	U	C	C			U	U		U	U	B	B	A
Fluorobenzene			A	A	U									
Fluorocarbon Oils			A	A	A		A	A		A		B	B	
Fluorolube		U	A	A	A		A	A				B	B	
Fluorinated Cyclic Ethers				A	A									
Fluosilicic Acid	A													
Formaldehyde			A	A	B	B	A	A	U	U		B	C	A
Formic Acid	A	A	A	A	B	B	A	A	U	A	B	C	A	
Freon 11	U	U	U	U	A	B	B	A	U	U	U	B	B	
Freon 12	B	A	B	B	A	A	A	A	A	A	U	C	B	
Freon 13	A	A	A	A	A	A	A	A	A	A	U	A	A	
Freon 21	U	U	U	U	U	B	B	U	U	U	U	U	U	
Freon 22	A	A	A	A	U	A	A	A	U	A	U	U	U	
Freon 31	B	B	A	A	U	A	A	B	A	B	U	U	U	
Freon 32	A	A	A	A	A		A	A		A			C	
Freon 112	U	U	U	U	B		B	B		A			A	
Freon 113	C	B	U	U	A	A	A	A	A	A	U	U	B	
Freon 114	A	A	A	A	A	A	A	A	A	A	U	U	B	
Freon 115	A	A	A	A	A	A	A	A	A	A	U	U	B	
Freon 142b	A	A	A	A	A		A	A		A			U	
Freon 152a	A	A	A	A	A		A	C		A			U	
Freon 218	A	A	A	A	A		A	A		A			U	
Freon C316	A	A	A	A	A		A	A		A			U	
Freon C318	A	A	A	A	A		A	A		A			A	
Freon 13B1	A	A	A	A	A		A	A		A			U	
Freon 114B2	U	C	U	U	B		A	A		A			A	
Freon 502	A	A	U	U	B		A	A		A			B	
Freon TF	C	B	U	U	A	A	A	A		A			A	
Freon T-WD602	C	B	A	B	B	A	B	B	A	A	U	U	A	
Freon TMC	B	C	B	B	B		B	B	A	A	C	A	A	
Freon T-P35	A	A	A	A	A		A	A	A	A	A	A	A	
Freon TA	A	A	A	A	A		A	A	A	A	A	A	C	
Freon TC	U	B	A	B	A		A	A	A	A	A	A	U	
Freon MF	U	B	B	U	A		C	U	C	A	A	A	A	
Freon BF	U	U	U	U	B		B	B	B	A	U	A	A	
Fuel Oil	A	A	U	U	A		B	B	B	A	A	A	A	
Fumaric Acid	A	A	U	U	A		A	A	A	A	A	A	A	
Furan, Furfuran	U	U	C	B	B		A	A	A	A	A	A	A	
Fufural	C	C	B	B	U		B	B	B	B	U	U	U	
Gallic Acid	A	B	B	B	B		B	B	U	A	A	A	U	
Gasoline	U	U	U	U	A		B	B	A	A	U	A	A	
Gelatin	A	A	A	A	A		A	A	A	A	A	A	A	
Glauber's Salt	A	A	B	B	B		A	A	A	A	A	A	A	
Glucose	A	A	A	A	A		A	A	A	A	A	A	A	
Glue	A	A	A	A	A		A	A	A	A	U	A	A	
Glycerin	A	A	A	A	A		A	A	A	B	A	A	A	
Glycols	A	A	A	A	A		A	A	B	A	A	A	A	
Green Sulfate Liquor	B	B	A	A	B		B	B	B	A	A	A	A	
Halowax Oil	U	U	U	U	U		U	U		A	U	A	A	
n-Hexaldehyde	U	U	B	A	U		A	B		B	B	A	A	
Hexane	U	U	U	U	U		B	B		A	B	U	A	
n-Hexene-1	U	U	U	U	U		B	B		A	B	U	A	
Hexyl Alcohol	A	A	C	C	A		B	B		U	B	A	A	
Hydrazine			A	A	B		B	B	U	A	C	C	A	
Hydraulic Oil (Petroleum)	U	U	A	A	A		A	B	A	U	C	C	A	
Hydrobromic Acid	A	C	A	A	U		A	B	A	U	C	C	A	
Hydrochloric Acid (Hot) 37%	U	U	C	C	U		U	B	C	U	U	U	A	
Hydrochloric Acid (Cold) 37%	B	B	A	A	B		B	A	B	U	B	B	A	
Hydrocyanic Acid	B	B	A	A	B		B	A	U	U	B	A	U	
Hydrofluoric Acid (Conc.) Hot	U	U	B	B	U		B	B	A	U	U	U	B	
Hydrofluoric Acid (Conc.) Cold	U	U	B	B	B		B	A	A	U	U	U	B	
Hydrofluoric Acid - Anhydrous	U	U	B	B	B		B	A	A	U	U	U	B	
Hydrofluosilicic Acid	A	B	A	A	B		B	A	A	U	U	U	A	



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:	A - Recommended - Little or minor effect B - Minor to moderate effect - Rubber parts probably still useful in many applications C - Moderate to severe effect - Rubber parts perhaps still useful in limited applications U - Not recommended Blank - No data or insufficient evidence - It should be noted that it is not expected that a polymer unrated would perform better than those that are rated.													
Fluid Resistance Key	(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSI	(13) FKM	(14) ACM
Hydrogen Gas	B	B	A	A	A		A	A	A	C	C	C	B	B
Hydrogen Peroxide (90%)	U	U	C	C	U					A	A	A	U	U
Hydrogen Sulfide (Wet) (Cold)	U	U	A	A	U	B	A	B	A	A	C	C	C	U
Hydrogen Sulfide (Wet) (Hot)	U	U	A	A	U	B	B	C	A	A	C	C	C	U
Hydroquinone	B	B	B	C										
Hypochlorous Acid	B	B	B	B	U	B								A
Iodine Pentafluoride	U	U	U	U	U	U	U	U	U	U	U	U	U	U
Iodoform														
Isobutyl Alcohol	A	B	A	A	B		A	B	B		A	B	A	A
Isooctane	U	U	U	A	A	A	B	B	B	A	U	B	A	U
Isophorone														
Isopropyl Acetate														
Isopropyl Alcohol	A	B	A	A	B	A	A	A	A	A	B	B	A	U
Isopropyl Chloride	U	U	U	U	U	B	B	B	B	A	U	A	A	U
Isopropyl Ether	U	U	U	U	B		B	B	B	A	U	A	C	
Kerosene	U	U	U	U	A	A	C	C	B	B	U	A	A	A
Lacquers	U	U	U	U	U	U	U	U	U	A	U	U	U	U
Lacquer Solvents	U	U	U	U	U	U	A	A	U	A	U	U	U	U
Lactic Acid	A	A	A	A	A									
Lard	U	U	U	U	A	A	C	C	A	U	B	A	A	A
Lavender Oil	U	U	U	U	B	A	B	C	B	B	B	B	A	B
Lead Acetate	A		A	A	B	B	B			U	U			
Lead Nitrate	A	A	A	A	B		A	A		B	B	A	A	U
Lead Sulfamate	B	B	A	A	B		A	A		U	B	A	A	A
Lime Bleach	A	A	A	A	A		B	B		U	B	A	A	U
Lime Sulfur	U	U	A	A	U		A	A		U	A	A	A	U
Lindol			A	A			C	C			C	C	B	
Linoleic Acid			U	U	B		U				A	B	A	A
Linseed Oil	U	U	B	B	A	A	B	B	B	A	C	B	A	A
Liquified Petroleum Gas	U	U	U	U	U	A	A	B	B	B	C	U	A	A
Lubricating Oils (Petroleum)	U	U	U	U	U	A	A	B	B	B	A	A	A	A
Lye	B	B	A	A	B		B	A	B	C	B	A	B	U
Magnesium Chloride	A	A	A	A	A	A	A	A	A	C	A	A	A	U
Magnesium Hydroxide	B	B	A	A	B	A	A	A	A	C	A	A	A	U
Magnesium Sulfate	B	B	A	A	A	A	A	A	A	B	A	A	A	U
Maleic Acid	B	B	C	C	A					B				
Maleic Anhydride	B	B	C	C										
Malic Acid			B	U	U	A	B	B	B		B	A	A	U
Mercuric Chloride	A	A	A	A	A	A	A	A	A	A				
Mercury	A	A	A	A	A	A	A	A	A					
Mesityl Oxide	U	U	B	B	U					A	U	U	A	U
Methane	U	U	U	U	A	A	B	B	B	B	B	B	A	A
Methyl Acetate	U	U	B	B	U	U	B	B						
Methyl Acrylate	U	U	B	B	B									
Methylacrylic Acid	U	U	B	B	B									
Methyl Alcohol	A	A	A	A	B	B	A	A	U	B	A	A	C	U
Methyl Bromide														
Methyl Butyl Ketone	U	U	A	A	U		U	B	B	A	B	U	U	U
Methyl Cellosolve	U	U	C	C	U	U	U	B	B		U	B	A	U
Methyl Chloride	U	U	U	U	U	U	U	C	U			B	B	
Methyl Cyclopentane	U	U	U	U	U	U	U	U	U					
Methylene Chloride	U	U	U	U	U	U	U	U	U	B				
Methyl Ethyl Ketone	U	U	A	A	U	U	U	B	B	A	B	U	U	U
Methyl Formate	U	U	B	C	U	U	U	B	B	B	B	C	U	U
Methyl Isobutyl Ketone	U	U	C	U	U	U	U	U	U	B	B	C	U	U
Methyl Methacrylate	U	U	B	B	U	U	U	B	U	B	B	B	U	U
Methyl Oleate	U	U	B	B	U	U	U	B	U	B	B	B	A	U
Methyl Salicylate														
Milk	A	A	B	B	A	A	A	B	B	A	B	A	A	A
Mineral Oil	U	U	U	U	U	U	U	U	U	B	B	B	B	U
Monochlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U	
Monomethyl Aniline	U	U	U	U	U	U	U	U	U	U	U	U	U	
Monoethanolamine	B	B	B	B	U		U	U	U	B	B	B	U	U
Monomethyl Ether	B	B	B	A	A									
Monovinyl Acetylene	B	B	A	A	A									
Mustard Gas	A	B	A	A	A									
Naphtha	U	U	U	U	U	C	A	C	U	C	B	U	B	B
Naphthalene	U	U	U	U	U	B				B	B	B	A	A
Naphthenic Acid	U	U	U	U	U					B	B	B	A	A

CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:		Chemical Resistance Guide													
		(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Natural Gas	C	C	U	U	A	A	A	A	B	B	A	C	A	A	B
Neatsfoot Oil	U	U	B	B	A	B	C	B	A	U	B	A	A	A	A
Neville Acid	U	U	B	B	C					A		B		A	
Nickel Acetate	A	A	A	A	A	B	A	A	A		A	U	U	U	U
Nickel Chloride	A	A	A	A	A	A	A	A	A		A	A	A	A	A
Nickel Sulfate	B	B	A	A	A	A	A	A	A		A	A	A	A	U
Niter Cake	A	A	A	A	A	A	A	A	A	C	A	A	A	A	U
Nitric Acid - Conc.	U	U	C	C	U	U	C	B	U	U	U	U	U	A	U
Nitric Acid - Dilute	U	U	B	B	U	U	A	A	U	U	B	B	B	A	U
Nitric Acid - Red Fuming	U	U	U	U	U	U	U	U	U	U	U	U	U	C	U
Nitrobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U	B	A
Nitrobenzine			C	C								A			
Nitroethane	B	B	B	B	U	U	C	C			U	U	U	U	U
Nitromethane	B	B	B	B	A	A	C	C			U	U	U	U	U
Nitrogen	A	A	A	A	A	U	A	A			A	U	U	U	A
Nitrogen Tetroxide	U	U	C	C	U	U	U	U			A	C	U	U	A
Octadecane	U	U	U	U	U	A	B	B	A	A	U	U	A	A	B
n-Octane	U	U	U	U	U	U	U	U	U	U	B	U	B	A	U
Octachlorotoluene	U	U	U	U	U	U	U	U	U	U	B	U	B	A	A
Octyl Alcohol	B	B	A	A	B	B	A	A	U	U	B	B	B	A	U
Oleic Acid	C	C	B	B	B	C	C	C	U	U	B	B	B	B	B
Oleum Spirits														B	A
Olive Oil	U	U	B	B	B	A	B	B	C		U	B	A	A	A
o-Dichlorobenzene	B	B	A	A	A	B	C	B	B		B	B	A	A	A
Oxalic Acid	B	B	A	A	A	B	B	B	B		B	B	A	A	A
Oxygen - Cold	B	B	A	A	A	B	B	B	A		B	B	A	A	A
Oxygen - 200 - 400° F.	U	U	U	U	U	U	U	U	U		U	A	U	B	B
Ozone	U	U	B	A	U	A	B	A	A		A	U	U	A	B
Paint Thinner, Duco	U	U	U	U	U	U	U	U	U		B	U	B	B	B
Palmitic Acid	B	B	B	B	B	A	B	B	B		U	A	A	A	A
Peanut Oil	U	U	C	C	C	A	A	B	B		U	U	A	A	A
Perchloric Acid	U	U	B	B	B	C	B	B	B		B	B	A	A	A
Perchloroethylene	U	U	U	U	U	C	B	U	U		U	B	B	B	A
Petroleum - Below 250	U	U	U	U	U	A	B	B	B		U	B	B	A	C
Petroleum - Above 250	U	U	U	U	U	B	B	C	C		U	C	B	B	A
Phenol	U	U	U	U	U	U	U	U	U		B	B	B	B	A
Phenylbenzene	U	U	U	U	U	U	U	U	U		B	B	B	B	A
Phenyl Ethyl Ether	U	U	U	U	U	U	U	U	U		B	B	A	B	A
Phenyl Hydrazine	A	B	C	C	U		C	C			C				A
Phorone			B	B											
Phosphoric Acid - 20%	B	C	A	A	B	U	B	A	A		U	B	A	A	A
Phosphoric Acid - 45%	U	U	B	B	B	U	B	B	B		U	B	A	A	A
Phosphorous Trichloride	U	U	A	A	A	U	B	U	U		U	B	A	A	A
Pickling Solution			C	C	U		C	C							
Picric Acid	B	B	B	B	B	B	A	B	B		U	B	A	B	U
Pinene	U	U	U	U	U	B	B	B	B		U	B	A	A	A
Pine Oil	U	U	U	U	U	B	B	B	B		B	B	A	A	U
Piperidine	U	U	U	U	U	U	U	U	U		U	B	A	U	U
Plating Solution - Chrome	U	U	A	A	A	A			C		U	U			A
Plating Solution - Others			A	A	A	A	B	B	A						A
Polyvinyl Acetate Emulsion			A	A	A	B	A	B	B						
Potassium Acetate	A	A	A	A	A	B	B	B	B				U	U	
Potassium Chloride	A	A	A	A	A	B	A	A	A		A	A	A	A	A
Potassium Cupro Cyanide	A	A	A	A	A	A	A	A	A		A	A	A	A	A
Potassium Cyanide	A	A	A	A	A	A	A	A	A		A	A	A	A	A
Potassium Dichromate	B	B	A	A	A	A	A	A	A		A	A	A	A	A
Potassium Hydroxide	B	B	A	A	A	B	A	A	A		B	B	C	C	B
Potassium Nitrate	A	A	A	A	A	A	A	A	A		A	A	A	A	A
Potassium Sulfate	B	B	A	A	A	A	A	A	A		B	A	A	A	U
Producer Gas	U	U	U	U	U	A	A	B	B		B	B	B	B	A
Propane	U	U	U	U	U	A	A	A	A		B	B	B	B	A
Propyl Acetate	U	U	U	B	B	U	U	U	U		B	B	B	B	U
n-Propyl Acetate	U	U	U	A	A	U	U	U	U		B	B	B	B	U
Propyl Alcohol	A	A	A	A	A	A	A	A	A		A	C	A	A	U
Propyl Nitrate			B	B	B	U						B	B	A	U
Propylene	U	U	U	U	U	U					B				
Propylene Oxide			B	B	B	U					U				
Pyranol	U	U	U	U	U	A	U	U	U		B	B	A	A	A
Pydrauls	U	U	B	B	U	U	U	U	U		B	B	A	A	U

CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:		Chemical Resistance Guide													
		(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Pyridine	U	U	B	B	U	U	U	U	U					U	
Pyroligneous Acid	C	C	B	B	U		B	B		B	U	B	B	U	U
Pyrrole	C	C	C	C			U			U				U	U
Radiation	B	B	U	B	B		B	B	A	U		C	U	U	B
Rapeseed Oil	U	U	A	A	B		B	B	B	U	A	A	A	A	B
Red Oil	U	U	U	U	A		B	B	A	A	U	A	A	A	A
Sal Ammoniac	A	A	A	A	A		A	A	A	A		B	A	A	A
Salicylic Acid	A	B	A	A	A							A	A	A	A
Salt Water	A	A	A	A	A							A	A	A	A
Sewage	B	B	B	B	A							B	A	A	U
Silicate Esters	U	U	U	U	B							B	A	A	
Silicone Greases	A	A	A	A	A							C	A	A	A
Silicone Oils	A	A	A	A	A							C	A	A	A
Silver Nitrate	A	A	A	A	A							C	A	A	A
Skydrol 500	U	U	B	A	U							C	C	U	U
Skydrol 7000	U	U	A	A	U							B	C	B	U
Soap Solutions	B	B	A	A	A							A	A	A	U
Soda Ash	A	A	A	A	A							A	A	A	U
Sodium Acetate	A	C	A	A	B							U	U	U	U
Sodium Bicarbonate	A	A	A	A	A							C	A	A	U
Sodium Bisulfite	A	B	A	A	A							A	A	A	U
Sodium Borate	A	A	A	A	A							A	A	A	A
Sodium Chloride	A	A	A	A	A							A	A	A	A
Sodium Cyanide	A	A	A	A	A							A	A	A	A
Sodium Hydroxide	A	A	A	A	B							B	B	B	A
Sodium Hypochlorite	C	C	B	B	B							B	B	B	U
Sodium Metaphosphate	A	A	A	A	A							U	A	A	A
Sodium Nitrate	B	B	A	A	B							B	U	A	A
Sodium Perborate	B	B	A	A	B							U	U	A	A
Sodium Peroxide	B	B	A	A	B							U	U	A	U
Sodium Phosphate	A	A	A	A	A							U	U	A	A
Sodium Silicate	A	A	A	A	A							A	A	A	A
Sodium Sulfate	B	B	A	A	A							A	A	A	U
Sodium Thiosulfate	B	B	A	A	B							A	A	A	U
Soybean Oil	U	U	C	C	A							B	A	A	A
Stannic(ous) Chloride	A	A	B	B	A							B	A	A	A
Steam Under 300° F.	U	U	A	A	U							U	U	U	U
Steam Over 300° F.	U	U	C	B	U							U	U	U	U
Stearic Acid	B	B	B	B	B							U	U	U	U
Stoddard Solvent	U	U	U	U	U							U	U	A	U
Styrene	U	U	U	U	U							C	A	B	A
Sucrose Solution	A	A	A	A	A							U	U	B	U
Sulfite Liquors	B	B	B	B	B							U	A	A	U
Sulfur	U	U	A	A	U							U	A	A	U
Sulfur Chloride	U	U	U	U	U							U	A	B	A
Sulfur Dioxide	C	C	B	A	U							U	A	B	U
Sulfur Hexafluoride	B	A	A	A	A							A	A	A	A
Sulfur Trioxide	C	U	B	B	U							B	B	B	A
Sulfuric Acid (Dilute)	U	C	B	B	U							U	C	A	U
Sulfuric Acid (Concentrated)	U	U	B	B	U							U	U	A	U
Sulfuric Acid (20% Oleum)	U	U	U	U	U							U	U	A	U
Sulfurous Acid	B	B	B	B	B							U	U	A	U
Tannic Acid	A	B	A	A	A							U	B	A	U
Tar, Bituminous	U	U	U	U	B							U	B	A	U
Tartaric Acid	A	B	B	B	A							U	A	A	A
Terpineol	U	U	C	C	B							U	A	A	A
Tertiary Butyl Alcohol	B	B	B	B	B							B	B	B	U
Tertiary Butyl Catechol	U	C	B	B	U							U	A	A	U
Tertiary Butyl Mercaptan	U	U	U	U	U								B	A	A
Tetrabromomethane	B	B	B	B	A								A	A	A
Tetrabutyl Titanate	B	B	B	B	B								B	A	A
Tetrachloroethylene	U	U	U	U	U								B	A	U
Tetraethyl Lead	U	U	U	B	B								B	A	U
Tetrahydrofuran	U	U	U	U	U								A	A	U
Tetralin	U	U	U	U	U								A	A	A
Thionyl Chloride	U	U	U	U	U								C	B	A
Titanium Tetrachloride	U	U	U	U	C								B	A	A
Toluene	U	C	C	A	A								U	B	A
Toluene Diisocyanate	C	C	C	A	A								U	B	A



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:		Chemical Resistance Guide													
		Chemical Resistance Guide													
Fluid Resistance Key		(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
Transformer Oil	U	U	U	U	A		B	B			B	A	A	A	B
Transmission Fluid Type A	U	U	U	U	A	A	B	B	A	A	B	A	A	A	A
Triacetin	B	C	A	A	B		B	B	U	B		U	U	U	U
Tributoxy Ethyl Phosphate	B	B	A	A	U		U	U	U	U	A		B	A	
Tributyl Phosphate	B	U	A	A	U		U	U	U	U	A		U	A	
Tributyl Mercaptan	U	U	U	U	U		U	U	U	U	U		U	A	
Trichloroethane	U	U	U	U	U		U	U	U	U	U	U	B	A	U
Trichloroacetic Acid	C	B	B	B	B		B	B			U	U	B	A	C
Trichloroethylene	U	U	U	U	C	U	U	U	U	U		B	B	A	
Tricresyl Phosphate	U	U	A	A	U	U	C	C	U	U		C	B	B	
Triethanol Amine	B	B	B	B	C	U	A	A	C	U		B	B	U	
Triethyl Aluminum														B	
Triethyl Borane														B	A
Trinitrotoluene	U	U	U	U	U		B	B			B		B	B	
Triocetyl Phosphate	U	U	A	A	U		U	U			C	C	B	B	U
Triaryl Phosphate	U	U	A	A	U		C	C			B	B	A	A	U
Tung Oil	U	U	C	U	A		B	B			B	B	B	A	
Turbine Oil	U	U	U	U	B	A	B	B			A	B	A	A	B
Turpentine	U	U	U	U	A	A	U	U	U		B	U	B	A	A
Unsymmetrical Dimethyl Hydrazine (UDMH)					A	A	B		A		U	U	U	U	
Varnish	U	U	U	U	B		C	C			A		B	A	
Vegetable Oils	U	U	A	A	A	A	B	B			A	C	A	A	A
Versilube	A	A	A	A	A	A	A	A			B	A	A	A	A
Vinegar	B	B	A	A	B		A	A			B	A	A	A	U
Vinyl Chloride					B		U	U							
Wagner 21B Fluid			A	B	A	C	A	B			U	C	U	U	
Water	A	A	A	A	A	A	B	A	A	A	A	A	A	A	UU
Whiskey, Wines	A	A	A	A	A	A	A	A	U	U	B	A	A	A	
White Pine Oil	U	U	U	U	U	B	U	U	U	U	B	A	A	A	
White Oil	U	U	U	U	B	A	B	B	B	B	A	U	A	A	A
Wood Oil	U	U	U	U	A		B	B			B	U	B	A	A
Xylene	U	U	U	U	U	U	U	U	U		C	B	U	A	A
Xylylenes	U	U	U	U	U	C	U	U	U		B	U	A	U	
Zeolites	A	A	A	A	A	A		A	A				A	A	
Zinc Acetate	A	C	A	A	B		B	B			U	U	U	U	U
Zinc Chloride	A	A	A	A	A	A	A	A			C	U	A	A	U
Zinc Sulfate	B	B	A	A	A	A	A	A			A	A	A	A	U
SPECIFICATION FLUIDS		Chemical Resistance Guide													
MIL-L-644B	C	C	C	C	A	A	C	C	C	A	C	C	A	A	B
MIL-L-2104B	U	U	U	U	A	A	A	A	A	A	A	A	A	A	A
MIL-L-2105B	U	U	U	U	A	A	A	A	A	A	A	A	A	A	A
MIL-G-2108	U	U	U	U	A	A	A	A	A	A	A	C	C	A	A
MIL-S-3136B	U	U	U	U	A	A	B	C	C	B	A	U	A	A	B
Type I	U	U	U	U	A	A	A	C	C	C	A	U	A	A	A
Type II	U	U	U	U	A	A	A	C	C	C	A	U	A	A	A
Type III	U	U	U	U	A	A	A	C	C	C	A	U	A	A	A
Type IV	U	U	U	U	A	A	A	A	A	A	C	A	A	A	A
Type IV	U	U	U	U	A	A	B	B	B	B	C	A	A	A	A
Type IV	U	U	U	U	A	A	C	C	C	C	A	U	A	A	A
MIL-L-3150A	U	U	U	U	A	A	A	A	A	A	A	C	A	A	A
MIL-L-3503	U	U	U	U	A	A	B	B	B	B	A	C	A	A	A
MIL-L-3545B	U	U	U	U	B	B	B	C	C	C	U	A	A	A	B
MIL-C-4339C	U	U	U	U	B	A	A	A	A	A	C	A	A	A	A
MIL-G-4343B	U	U	U	C	C	B	B	B	B	B	A	U	B	A	A
MIL-L-5020A	U	U	U	U	A	A	A	B	C	B	A	U	A	A	B
MIL-J-5161F	U	U	U	U	A	A	C	C	C	C	A	U	A	A	A
MIL-C-5545A	U	U	U	U	B	B	B	C	C	C	U	A	A	B	C
MIL-H-5559A	B	A	A	A	B	B	B	B	B	B	B	B	B	B	B
MIL-F-5566	A	A	A	A	A	B	B	B	B	B	A	A	A	A	A
MIL-F-5602	U	U	U	U	A	A	B	B	B	B	A	C	A	A	A
MIL-H-5606B	U	U	U	U	A	A	B	B	B	B	A	U	A	A	A
MIL-J-5624G	U	U	U	U	A	A	C	C	C	C	A	U	A	A	B
Grade JP-3	U	U	U	U	A	A	C	C	C	C	A	U	A	A	B
Grade JP-4	U	U	U	U	A	A	C	C	C	C	A	U	A	A	B
Grade JP-5	U	U	U	U	A	A	B	B	B	B	A	U	A	A	B
MIL-O-6081 C	U	U	U	U	A	A	B	B	B	B	A	C	A	A	A



CHEMICAL RESISTANCE GUIDE

Chemical Effect Rating:

A - Recommended - Little or minor effect

B - Minor to moderate effect - Rubber parts probably still useful in many applications

C - Moderate to severe effect - Rubber parts perhaps still useful in limited applications

U - Not recommended

Blank - No data or insufficient evidence - It should be noted that it is not expected that a polymer unrated would perform better than those that are rated.

Fluid Resistance Key	(1) NR IR	(2) SBR BR	(3) IIR	(4) EPM EPDM	(5) NBR	(6) CO ECO	(7) CR	(8) CSM	(9) AU EU	(10) T	(11) Si	(12) FSi	(13) FKM	(14) ACM
MIL-L-6082C	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-H-6083C	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-L-6085A	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-L-6086B	U	U	U	U	A	A	C	A	A	B	C	A	A	A
MIL-L-6387A	U	U	U	U	A	B	C	C	B	B	C	A	A	A
MIL-C-6529C	U	U	U	U	B	B	B	C	C	C	U	A	A	B
MIL-F-7024A	U	U	U	U	A	A	B	C	B	A	U	A	A	B
MIL-H-7083A	B	A	A	A	A	B	C	C	C	C	B	B	B	C
MIL-G-7118A	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-G-7187	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-G-7421A	U	U	U	U	A	B	C	C	B	B	C	A	A	A
MIL-H-7644	B	A	B	A	B	B	B	B	C	C	U	B	A	B
MIL-L-7645	U	U	U	U	B	B	B	C	C	C	U	A	A	B
MIL-G-7711A	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-7808F	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-L-7870A	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-C-8188C	U	U	C	U	A	B	B	B	C	B	C	A	A	C
MIL-A-8243B	B	A	A	A	A	B	B	B	C	C	B	B	B	C
MIL-L-8383B	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-H-8446B	U	U	U	U	B	C	B	B	A	B	C	A	A	C
MIL-I-8660B	A	A	A	A	A	A	A	A	A	A	U	A	A	B
MIL-L-9000F	U	U	U	U	A	A	B	C	C	B	U	A	A	U
MIL-T-9188B	U	U	A	A	U	U	U	U	U	U	U	C	U	U
MIL-L-9236B	C	C	C	C	A	B	C	C	B	B	U	U	C	A
MIL-L-10295A	U	U	U	U	A	A	B	B	B	B	C	A	A	A
MIL-L-10324A	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-G-10924B	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-L-11734B	U	U	U	C	U	A	B	C	C	B	C	A	A	C
MIL-O-11773	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-P-12098	B	A	B	A	B	B	B	B	C	C	U	B	A	B
MIL-H-13862	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-H-13866A	U	U	B	A	B	B	B	B	B	A	C	A	A	A
MIL-H-13910B	B	A	B	A	B	B	B	B	C	C	U	B	A	B
MIL-H-13919A	U	U	U	U	A	B	B	B	B	A	C	A	A	A
MIL-L-14107B	U	U	U	U	C	A	A	A	A	U	A	A	A	A
MIL-L-15017	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-15018B	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-15019C	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-15719A	C	B	B	B	B	B	B	B	C	B	U	B	A	B
MIL-G-15793	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-F-16929A	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-L-16958A	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-F-17111	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-L-17331D	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-17353A	U	U	U	U	A	B	C	C	B	B	C	A	A	A
MIL-L-17672B	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-18486A	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-G-18709A	U	U	U	A	A	U	U	U	U	U	C	A	A	U
MIL-H-19457B	U	U	U	U	A	A	U	U	U	U	C	A	U	U
MIL-F-19605	U	U	U	U	A	A	C	C	C	A	U	A	A	A
MIL-L-19701	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-L-21260	U	U	A	A	A	A	A	A	A	A	C	A	A	A
MIL-S-21568A	B	A	A	A	A	A	B	B	B	C	U	B	A	A
MIL-H-22072	B	A	A	A	A	B	B	B	B	C	B	B	B	C
MIL-L-22396	U	U	U	U	A	A	A	A	A	A	C	A	A	A
MIL-L-23699A	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-G-23827A	U	U	A	A	A	A	B	B	B	B	C	A	A	C
MIL-G-25013D	B	A	A	A	A	A	B	B	B	B	U	B	A	B
MIL-F-25172	U	U	U	U	A	A	C	C	C	B	U	A	A	A
MIL-L-25336B	U	U	C	U	A	B	C	C	C	B	C	A	A	C
MIL-F-25244A	U	U	U	U	A	A	C	C	C	A	U	A	A	C
MIL-G-25537A	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-F-25558B	U	U	U	U	A	A	B	B	B	A	C	A	A	A
MIL-F-25576C	U	U	U	U	A	A	C	C	C	A	U	A	A	A
MIL-H-2598	U	U	U	U	A	A	B	B	B	B	C	A	A	A
MIL-H-25598	U	U	U	U	A	A	B	B	B	B	C	A	A	A
MIL-F-25656B	U	U	U	U	A	A	C	C	C	A	U	A	A	A
MIL-L-25681C	B	C	C	C	A	B	C	C	C	B	U	B	A	B
MIL-G-25760A	C	C	C	C	A	B	C	C	C	B	U	A	A	C



CHEMICAL RESISTANCE GUIDE